

Parameter	Unit	Nut coke	Industrial- domestic coke	Pea coke I	Pea coke II	Pea coke	Coke breeze
Granulation	mm	20-40	+40	10-25	10-20	5-25	0-10
Calorific value Q_{rj} (min)	kJ/kg	28100	28000	25100	24000	25100	23700
Total moisture W_{rt} (max)	%	12,0	7,0	15,0	15,0	16,0	17,0
Ash A^d (max)	%	11,5	11,5	12,5	12,5	12,5	13,5
Volatile matter V^{daf} (max)	%	1,2	1,2	1,4	1,4	1,4	2,0
Sulphur S^d_t (max)	%	0,6	0,6	0,7	0,7	0,7	0,7
Phosphorus P^a (max)	%	0,7	0,06	0,07	0,07	0,07	0,07
Undersize grain (max)	%	10,0	10,0	8,0	10,0	10,0	
Oversize grain (max)	%	10,0		8,0	10,0	10,0	16,0
Strenght M40 (min)	%		50,0				
Abrasion M10 (max)	%		8,0				