

Parameter	Unit	Industrial coke
Granulation	mm	25-80
Calorific value Q_f^r (min)	kJ/kg	27500
Total moisture W_t^r (max)	%	6,0
Ash A^d (max)	%	10,0
Volatile matter V^{daf} (max)	%	0,70
Sulphur S_t^d (max)	%	0,5
Carbon fix C_{fixd}	%	89,0
Phosphorus P^a (max)	%	0,06
Undersize grain (max)	%	4,0
Oversize grain (max)	%	5,0
Strenght M40 (min)	%	73,0
Abrasion M10 (max)	%	6,0