

Parameter	Unit	Foundry coke				
		60-90	+80	80-140	+100	70-100
Granulation	mm	60-90	+80	80-140	+100	70-100
Calorific value Q_{rj} (min)	kJ/kg	27700	28950	29100	29140	28950
Total moisture W_{rt} (max)	%	8,0	6,0	4,5	2,0	6,0
Ash A^d (max)	%	10,5	10,5	10,5	10,5	10,5
Volatile matter V^{daf} (max)	%	1,5	1,3	1,3	1,2	1,3
Sulphur S_{dt} (max)	%	0,8	0,7	0,7	0,7	0,7
Undersize grain (max)	%		15,0	10,0	10,0	10,0
Oversize grain (max)	%			10,0		10,0
Strenght M40 (min)	%	85,0	85,0	85,0	85,0	85,0
Abrasion M10 (max)	%	7,0	8,0	8,0	10,0	8,0
Phosphorus P^a (max)	%		0,04	0,04	0,04	0,04
Oversize grain (max)	%			10,0		10,0